

LUXOR®/ALUFIN® MC Pro

Easy to process stamping foil that combines high coverage and gloss with clean stamping.

The advantages at a glance

- ideal combination of high coverage and clean stamping
- very good gloss
- good adhesion even at low temperatures and low pressure
- easy make-ready, good workability
- high abrasion resistance
- good overprintability with conventional lacquers and inks
- processable on all commercially available stamping machine systems

Application examples

- Folding boxes, sheet-fed labels, all kinds of self-adhesive labels, greeting cards, paperback bindings, advertising materials.

Processing temperatures

- 90 - 100 °C / 194 - 212 °F on vertical and platen presses
- 140 - 170 °C / 284 - 338 °F on cylinder presses
- 150 - 220 °C / 302 - 428 °F on rotary stamping units





LUXOR 420



LUXOR 425



LUXOR 427



LUXOR 428



LUXOR 396



LUXOR 397