

## LUXOR®/ALUFIN® AF

Clean cutting KURZ standard quality for synthetic leather book covers and soft PVC.

### Main Characteristics

- for fine line details on synthetic book cover materials with smooth surfaces such as for example Balacron, Guaflex, Skivertex, Reluskin, Kivar etc.
- very high gloss
- good results in plasticizer migration tests

### Fields of Application

- Nitrocellulose or PVC based book covers,
- PVC folders and covers,
- pocket diaries and
- jewelry boxes

### Stamping Temperatures

- 105 - 115 °C (221 - 239 °F) e.g. on Kolbus machines



ALUFIN Special



LUXOR 220



LUXOR 385



LUXOR 428

## LUXOR®/ALUFIN® AS

Standard quality for broad area stampings on smooth or grained synthetic book cover materials

Standard quality for broad area stampings on smooth or grained synthetic book cover materials.

### Main Characteristics

- easy release
- for medium and broad area designs
- good coverage even on medium to heavy grained synthetic leather
- very high gloss
- good results in plasticizer migration tests

### Fields of Application

- Nitrocellulose or PVC based book covers,
- pocket diaries and
- other synthetic leather bindings

### Stamping Temperatures

- 100 - 110 °C (212 - 230 °F) e.g. on Kolbus Machines



## LUXOR®/ALUFIN® AB

Standard quality for bookbinding with exceptional coverage on woven fabrics and linen.

### Main Characteristics

- multi-purpose quality with good coverage on cloth bindings
- suitable for embossed and solid area designs

### Fields of Application

- Bookbinding material

### Stamping Temperatures

- 100 - 105 °C (212 - 221 °F) for example on Kolbus machines



ALUFIN Special



ALUFIN Mat



LUXOR 220



LUXOR 420



LUXOR 428

# LUXOR®/ALUFIN® GFM 14066

Standard quality for edge gilding

Standard quality for edge gilding.

## Main Characteristics

- good adhesive strength and no flaking when book is opened
- suitable for untreated or primed material

## Priming advice:

- 50 g shellac, 50 g cholophonium, 1 liter ethanol

## Fields of Application

- Pocket diaries,
- bibles,
- hymn books,
- special editions,
- encyclopedias

## Stamping Temperatures

- 120 - 140 °C (248 - 284 °F) with Ochsner, Gilmore, Dukat or Carat edge gilding machines

